

Purolite® A200

Gel Type II Strong Base Anion Exchange Resin

PRODUCT DATA SHEET

Purolite A200 is a clear gel-type strong-base anion exchanger containing Type II quaternary ammonium groups. It has excellent operating capacity and good kinetics even when regenerant levels are comparatively low. It also rinses very efficiently after regeneration. It shows good resistance to physical and osmotic shock in normal operation. It is particularly useful in treating feed-waters with a high proportion of Free Mineral Acidity, and in addition it has high reversible sorptive capacity for the complex organic materials, both ionized and un-ionized, which occur in many surface water supplies. Specially tailored size grades may be used with excellent results in most of the usual ion-exchange column configurations, but they are particularly suitable for deionizing waters in counter-flow operation, where, rinse volumes represent a marked improvement over those of the classical Type II, **Purolite A300**, for example. In a conventional two-stage deionizing plant, its silica-removal properties are comparable with those of any premium Type II strong-base anion exchanger; however, as with other resins of this type, a polishing mixed-bed is necessary to ensure the lowest levels of residual silica.

Typical Physical and Chemical Characteristics

Application	Demineralization with High Regeneration Efficiency
Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Type II Quaternary Ammonium
Ionic Form as Shipped	Cl ⁻
Total Capacity (min.)	1.3 eq/l (28.4 Kgr/ft ³) (Cl ⁻ form)
Moisture Retention	45 - 51 % (Cl ⁻ form))
Particle Size Range	300 - 1200 µm
<300 µm (max.)	1 %
Uniformity Coefficient (max.)	1.7
Reversible Swelling, Cl ⁻ → OH ⁻ (max.)	15 %
Specific Gravity	1.08
Shipping Weight (approx.)	680 - 715 g/l (42.5 - 44.7 lb/ft ³)
Temp Limit, Cl ⁻ Form	85°C (185°F)
Temp Limit, OH ⁻ Form	35°C (95°F)



Americas
 T +1 610.668.9090
 F +1 484.384.2751
 americas@purolite.com

Europe
 T +44 1443 229334
 F +44 1443 227073
 europe@purolite.com

Asia Pacific
 T +86 571 876 31382
 F +86 571 876 31385
 asiapacific@purolite.com